



SensiCare Ice[®] Nitrile Gloves

POWDER FREE, NON -STERILE, AMBIDEXTROUS EXAM GLOVES

References	486800 - XS 486802 - M	486801 - S 486803 - L	486804 - XL																																	
Primary Material	Nitrile																																			
Color/Grip	Blue / Fingertip texture																																			
Thickness	<table border="1"> <tr> <td>Single Wall</td> <td>mm</td> </tr> <tr> <td>Fingertip</td> <td>0.09</td> </tr> <tr> <td>Palm</td> <td>0.07</td> </tr> <tr> <td>Cuff</td> <td>0.05</td> </tr> </table>			Single Wall	mm	Fingertip	0.09	Palm	0.07	Cuff	0.05																									
Single Wall	mm																																			
Fingertip	0.09																																			
Palm	0.07																																			
Cuff	0.05																																			
Cuff Design	Beaded																																			
Accelerators	Carbamates and MBT																																			
EN 455 Test Results	<p>Testing performed by an ISO 17025 accredited laboratory</p> <table border="1"> <thead> <tr> <th>EN 455 - 1</th> <th>Test Results</th> <th>EN 455 Requirement</th> </tr> </thead> <tbody> <tr> <td>Freedom From Holes</td> <td>Complies</td> <td>AQL 1.5</td> </tr> <tr> <th>EN 455 - 2</th> <th>Test Results</th> <th>EN 455 Requirement</th> </tr> <tr> <td>Dimensions (length)</td> <td>241 mm</td> <td>≥ 240 mm median</td> </tr> <tr> <td>Dimensions (width)</td> <td>95 mm</td> <td>95 ± 10 mm median</td> </tr> <tr> <td>Force at break before accelerated aging</td> <td>6.5 N</td> <td>≥ 6.0 N</td> </tr> <tr> <td>Force at break after accelerationg aging <i>(7 days at 70 °C in an oven)</i></td> <td>6.2 N</td> <td>≥ 6.0 N</td> </tr> <tr> <th>EN 455 - 3</th> <th>Test Results</th> <th>EN 455 Requirement</th> </tr> <tr> <td>Powder Content</td> <td>0.40 mg/glove</td> <td>≤ 2 mg/glove</td> </tr> <tr> <td>Protein Content</td> <td>Not Tested</td> <td>Not required</td> </tr> <tr> <th>EN 455 - 4</th> <td colspan="2">SensiCare Ice meets EN 455-4 Requirements and testing for shelf life determination</td> </tr> </tbody> </table>			EN 455 - 1	Test Results	EN 455 Requirement	Freedom From Holes	Complies	AQL 1.5	EN 455 - 2	Test Results	EN 455 Requirement	Dimensions (length)	241 mm	≥ 240 mm median	Dimensions (width)	95 mm	95 ± 10 mm median	Force at break before accelerated aging	6.5 N	≥ 6.0 N	Force at break after accelerationg aging <i>(7 days at 70 °C in an oven)</i>	6.2 N	≥ 6.0 N	EN 455 - 3	Test Results	EN 455 Requirement	Powder Content	0.40 mg/glove	≤ 2 mg/glove	Protein Content	Not Tested	Not required	EN 455 - 4	SensiCare Ice meets EN 455-4 Requirements and testing for shelf life determination	
EN 455 - 1	Test Results	EN 455 Requirement																																		
Freedom From Holes	Complies	AQL 1.5																																		
EN 455 - 2	Test Results	EN 455 Requirement																																		
Dimensions (length)	241 mm	≥ 240 mm median																																		
Dimensions (width)	95 mm	95 ± 10 mm median																																		
Force at break before accelerated aging	6.5 N	≥ 6.0 N																																		
Force at break after accelerationg aging <i>(7 days at 70 °C in an oven)</i>	6.2 N	≥ 6.0 N																																		
EN 455 - 3	Test Results	EN 455 Requirement																																		
Powder Content	0.40 mg/glove	≤ 2 mg/glove																																		
Protein Content	Not Tested	Not required																																		
EN 455 - 4	SensiCare Ice meets EN 455-4 Requirements and testing for shelf life determination																																			
EN 374 Test Results	<p>Testing performed by an ISO 17025 accredited laboratory</p> <table border="1"> <thead> <tr> <th>EN 374 -1</th> <th>Test Results</th> <th>EN 374 Requirement</th> </tr> </thead> <tbody> <tr> <td>Minimum Liquid Proof Length</td> <td>Pass</td> <td></td> </tr> <tr> <td></td> <td>Size XS/S/M/L/XL</td> <td></td> </tr> <tr> <th>EN 374 - 2</th> <th>Test Results</th> <th>EN 374 Requirement</th> </tr> <tr> <td>Air Leak Test</td> <td>Pass</td> <td>AQL 1.5</td> </tr> <tr> <td>Water Leak Test</td> <td>Pass</td> <td>AQL 1.5</td> </tr> </tbody> </table>			EN 374 -1	Test Results	EN 374 Requirement	Minimum Liquid Proof Length	Pass			Size XS/S/M/L/XL		EN 374 - 2	Test Results	EN 374 Requirement	Air Leak Test	Pass	AQL 1.5	Water Leak Test	Pass	AQL 1.5															
EN 374 -1	Test Results	EN 374 Requirement																																		
Minimum Liquid Proof Length	Pass																																			
	Size XS/S/M/L/XL																																			
EN 374 - 2	Test Results	EN 374 Requirement																																		
Air Leak Test	Pass	AQL 1.5																																		
Water Leak Test	Pass	AQL 1.5																																		
Chemical Resistance	SensiCare Ice Nitrile Exam Gloves resistance to common chemicals has been assessed in accordance to EN 374-3. Results can be obtained upon request.																																			



Medline Industries Inc.
www.medline.com

© 2011 Medline Industries, Inc. Medline and SensiCare Ice are registered trademarks of Medline Industries Inc.



SensiCare Ice® Nitrile Gloves

POWDER FREE, NON -STERILE, AMBIDEXTROUS EXAM GLOVES

EN 420 Test Results	Testing performed by an ISO 17025 accredited laboratory		
		Test Results	EN 420 Requirement
	Size XS/S/M/L/XL	Pass	
	Dexterity (performance level 5)	Pass	
	pH Value (pH value of the 2% aqueous extract)	7.37	3.5 < pH < 9.5
Viral Penetration	Tested and passed in accordance with ASTM F1671		
Elongation	ASTM D6319	Test Results	ASTM D6319 Requirement
		Before Aging	550%
		After Aging	444%
Storage Conditions	Protect from freezing. Avoid excessive heat. Keep dry. Product should be shielded from direct sunlight, fluorescent lighting, x-rays, moisture and ozone.		
Packaging	200 each/box - 10 boxes/case - 2000 each/case (XL - 180 each/box, 1800 each/case)		
Expiration Date	35 months from date of manufacture.		
Manufactured For	Medline Industries, Inc.		
Made In	Malaysia		
Manufacturer	is certified to EN ISO 13485		
Quality Standards and Regulations	Conforms to EU Directive 93/42/EEC - Class I Non Sterile. Products meet the requirements of European harmonized standards EN 455-1, EN 455-2, EN 455-3 and EN 455-4		



Latex free

Medline Industries Inc.

www.medline.com

© 2011 Medline Industries, Inc. Medline and SensiCare Ice are registered trademarks of Medline Industries Inc.

Page 2 of 2